

## BOREAL NATURE ELITE

Boreal Nature Elite is a closed-cell, medium-density spray polyurethane foam insulation, formulated with environmentally responsible HFO blowing agents. The product is manufactured without ozone-depleting substances (Zero ODS) and contains negligible Global Warming Potential (GWP) substances.

Tested by independent laboratories, Boreal Nature Elite meets multiple compliance standards, including CAN/ULC S705.1.15 for insulation and vapour barrier, CCMC 07 26 23.01 for radon control, CCMC 07 27 09.01 for air barrier systems, ASTM E84 for Class One foam, and CAN/ULC S134 for fire-rated exterior walls.

PHYSICAL PROPERTIES - CCMC #14140-L			
PHYSICAL PROPERTIES	STANDARD	RESULT	
Core Density	ASTM D1622	2.0 lb/ft <sup>3</sup>	32 kg/m <sup>3</sup>
Compressive Strength	ASTM D1621	33.1 psi	228 kPa
Tensile Strength	ASTM D1623	29.7 psi	205 kPa
Water Vapour Permeance @50mm	ASTM E96-A	34 ng/Pa.s.m <sup>2</sup>	
Surface Burning (flame spread index)	CAN/ULC S127-14	Less than 500	
Fungi Resistance	ASTM C1338	No growth	
Long Term Thermal Resistance			
Thickness 25 mm			0.93 RSI
Thickness 50 mm	CAN/ULC- S770-09		1.96 RSI
Thickness 75 mm			2.93 RSI
Thickness 100 mm			4.12 RSI
Air Permeance	ASTM E2178	0.001 L/(s.m <sup>2</sup> )	
Recommended Time to Occupancy	CAN/ULC S774	25 hours	
Open Cell Content	ASTM D6226 (Procedure 2)	2.8 %	
Water Absorption (volume)	ASTM D2842 (Procedure A)	1.6 %	
Dimensional Stability	ASTM D2126 (28 days) -20°C 80°C 70°C, 97% RH (±3%)	-1 % +2 % +13 %	

PHYSICAL PROPERTIES – Additional testing		
Radon mitigation system	CCMC Masterformat 07 26 23.01	CCMC #14445-R
Air Barrier System	CCMC Masterformat 07 27 09.01	CCMC #14241-R
Fire Test of Exterior Wall Assemblies	CAN/ULC S134	Pass
Surface Burning Characteristics	ASTM E84	Class 1
15 minutes wall assembly high heat	NBC, Art. 3.2.3.8 Protection Exterior Building Face, Sentence 2 CAN/ULC S101 15-min. Stay In Place test.	Met the requirements on three different wall designs. Independent laboratory report upon request.
Initial Thermal Resistance *	ASTM C-518 (CAN/ULC S770) 10 days 23°C and 50% R.H.	2.49 RSI (R 7.2/in)

\*Independent testing verified that Boreal Nature Elite R-value varies by less than 3% from the initial thermal resistivity value when samples were conditioned for 180 days. (23°C and 50% R.H)







RECYCLED AND RENEWABLE CONTENT	
Recycled Content	17.4 %
Renewable Materials Content (Veg. oils)	5.8 %

LONG TERM THERMAL RESISTANCE (CAN/ULC S770-09)		
THICKNESS mm (in)	R-VALUE (ft <sup>2</sup> .hr.°F)/Btu	RSI (m <sup>2</sup> .K)/W
50.8 (2.00)	11.4	2.0
63.5 (2.50)	14.3	2.5
76.2 (3.00)	17.4	3.1
88.9 (3.50)	20.6	3.6
102.0 (4.00)	24.1	4.2
127.0 (5.00)	30.7	5.4
152.0 (6.00)	36.5	6.4
177.8 (7.00)	42.7	7.5
203.2 (8.00)	48.9	8.6

COMPONENT PRODUCT SPECIFICATIONS		
PROPERTIES	ISOCYANATE - A-2732	RESIN - BOREAL NATURE ELITE
Colour	Brown Liquid	Green Liquid
Viscosity at 25°C	150 – 250 cps	280 - 420 cps
Specific Gravity at 25°C	1.22 – 1.25	1.17 – 1.23
Shelf Life	12 months	6 months
Storage Temperature	15-35°C / 59-95°F	15-25°C / 59-77°F
Ratio (volume)	100	100

INSTALLATION GUIDELINES					
Boreal Nature Elite	Ambient Temperatures		Spray Temperatures		Minimum Spray Pressure
Summer	50°F to 95°F	10°C to 35°C	95°F to 120°F	35°C to 49°C	
Regular	32°F to 68°F	0°C to 20°C	95°F to 120°F	35°C to 49°C	
Winter	14°F to 50°F	-10°C to +10°C	100°F to 130°F	38°C to 55°C	

Additional Information
<ul style="list-style-type: none"> <li>Maximum thickness per pass must not exceed 50 mm (2 inches) due to excessive exothermic heat, which may ignite the foam in extreme cases.</li> <li>Two successive passes of 50 mm are possible. Wait 2 hours before a third pass, or until the internal foam temperature is below 37°C (100°F).</li> <li>Maximum installed thickness in 24 hours must not exceed 200mm (8 inches).</li> <li>Product is combustible and must be installed in accordance with applicable building codes.</li> <li>The service temperature is between -60°C and 80°C.</li> <li>Consult the Safety Data Sheet before handling the chemicals (available online).</li> <li>Temperature, humidity, equipment, substrate can vary installation parameters.</li> <li>In application vehicle, store components A and B between 18-24°C for best performance.</li> </ul>

Accreditations & Certifications	
	Canadian Code Compliance
	Radon Barrier
	Air Barrier System
	
	
	

The information herein is considered an accurate description of product performance at the time of printing. Genyk Inc. disclaims liability for incidental or consequential damages resulting from inappropriate use of this product. It is the user's responsibility to test the product. No information herein is to be considered as permission or recommendation to infringe on any patent or intellectual property. Boreal Nature Elite must be applied by licensed installers in accordance with the CAN/ULC S705.2 application standard.