



# Elite 2.0

## Closed Cell, medium density HFO blown spray foam

ELITE 2.0 is a medium density spray-applied rigid polyurethane foam system insulation formulated without ozone depletion substances (Zero ODS). ELITE 2.0 is made with **HFO** and has a global warming potential (GWP) of 1, which is 99.9% lower than current HFC used in this industry. The product complies with the International Code Council's AC377 standard and obtains high ranked results to ASTM E84 fire testing. It is a high-performance insulation and air barrier, ideal for new construction and retrofit insulation of residential and commercial buildings.

The ELITE 2.0 is offered in a choice between a neutral color or the renowned Genyk lime green color.

TYPICAL PHYSICAL PROPERTIES		
PHYSICAL PROPERTIES	STANDARD	RESULT
<b>Aged R-Value</b>	ASTM C 518	7.0 @ 1" 25 @ 3.5"
<b>Core Density</b>	ASTM D1622	2.00 lb/ft <sup>3</sup>
<b>Compressive Strength</b>	ASTM D 1621	26 psi
<b>Tensile Strength</b>	ASTM D1623	29 psi
<b>Water Vapour Transmission (permeance @ 1.5")</b>	ASTM E96	0.70 perm
<b>Water Absorption</b>	ASTM D2842	< 2%
<b>Fungi Resistance</b>	ASTM C1338	No growth
<b>Closed Cell Content</b>	ASTM D 2856	>98%
<b>Dimensional Stability (14 days 70°C, 97±3% RH)</b>	ASTM D2126	3 %
<b>Air Leakage (75 Pa @ 1")</b>	ASTM E283M	< 0.02 L/sm <sup>2</sup>
<b>Re-Entry Time</b>	ASTM D8445	1 hr (10 ACH)

FIRE PERFORMANCE CHARACTERISTICS		
<b>ASTM E 84</b>	Surface Burning Characteristics, 4" Thick Flame Spread Index Smoke Developed	Class1 10 280
<b>AC 377 Appendix X</b>	Without an intumescent coating	Meets Criteria
<b>NFPA 286</b>	With 15 mils (dry) DC-315 14 mils (WFT) No Burn Plus thB	Meets Criteria

**THERMAL RESISTANCE (R-VALUES)**

THICKNESS (inches)	R-VALUE (°F.ft <sup>2</sup> .h/Btu)
1	7
2	14
3.5	25
4	29
5	36
6	43
7	50
8	57
9	65
10	72

Calculated R-values are based on tested K-values at 1- and 3.5-inch. R-values greater than 10 are rounded to the nearest whole number.

**APPLICATION GUIDELINES**

- Maximum single pass thickness: 3" (to avoid fire hazards resulting from excessive heat generation)
- If more than 3 inches is required, use multiple passes of 2 inches. Second layer can be applied after first is hard to the touch.
- If subsequent passes are needed, wait until internal temperature of installed pass be less than 100°F before installing subsequent passes. Maximum thickness during 24-hour period is 8 inches.

**APPLICATION PARAMETERS**

ELITE 2.0	Ambient Temperatures	Spray Temperatures	Recommended Spray Pressure
Summer	45°F to 95°F	100°F - 120°F	900 - 1200 psi
Regular	30°F to 70°F		
Winter	15°F to 60°F		

Processing conditions can vary depending on temperature, humidity, substrate, equipment, and other factors. It is the applicator's responsibility to process and apply Elite 2.0 within specification.



During the application, it is important not to exceed 3 inches per pass, in order not to alter the quality of the foam.



Before handling these chemicals, please consult the Safety Data Sheet for the two components, that are available from Genyk.

**COMPONENT PRODUCT SPECIFICATIONS**

PROPERTIES	A - PMDI ISOCYANATE	ELITE 2.0 RESIN
Colour	Brown Liquid	Color options: Green or Amber Liquid
Viscosity at 25°C	150 – 250 cps	300 – 600 cps
Specific Gravity at 25°C	1.22 – 1.25	1.17 – 1.22
Shelf Life	12 months	6 months
Storage Temperature	50°F - 100°F	50°F - 77°F
Ratio (volume)	100	100

The information contained herein is based on information available to Genyk Inc. The data is considered an accurate description of the product performance and is presented in good faith. However, Genyk Inc. disclaims any liability for incidental or consequential damages which may result from the inappropriate use of this product. It is the user's responsibility to thoroughly test the product in any application to determine performance, efficiency and safety. No information contained herein is to be considered as permission or recommendation to infringe on any patent or other intellectual property.